



材料及工程實驗室-台中



Testing Laboratory
0292

試驗報告



報告編號：TV-16-00546Z

頁數：1 OF 2

報告日期：105年02月15日

委託單位：宏庚興業有限公司
 產品名稱：HG 水性抗UV塗裝板
 製造廠商：宏庚興業有限公司
 供應廠商：宏庚興業有限公司
 收件日期：105年02月04日
 試驗日期：105年02月04日~105年02月15日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗要求：

耐候性試驗-紫外線照射 200 小時

試驗方法：


ASTM G154-12a Standard Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials

試驗結果：

- 請詳附件 -

---1---

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：TV-16-00546Z

頁數：2 OF 2

報告日期：105年02月15日

試驗儀器：

儀器名稱	廠牌	型號
紫外線耐候試驗機	Q-LAB	QUV/Spray

試驗結果：

試驗項目	試驗結果
耐候性試驗200 hrs.	表面無龜裂、膨脹、剝離等缺點

註：耐候試驗條件：依據ASTM G154-12a (Cycle 1)

照度：0.89W/m²/m

燈源種類：UVA-340

循環條件：8h UV at 60±3 °C Black Panel Temperature;

4h Condensation at 50±3°C Black Panel Temperature

--- oOo ---

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.